



#866H Clear Gloss High Adhesion 1.9 Mil PP Self Wound Lamination

Item	# 866H clear gloss BOPP high adhesion self wound lamination.
Description	1.2 mil BOPP clear film with 0.7 mil hot melt synthetic rubber adhesive for higher adhesion.
Applications	For prime paper or film labels, under lamination and other applications that need high adhesion levels.

Product Data

Effective 09/08/10

Film	1.2 mil clear gloss polypropylene	PSTC-33
Adhesive	0.7 mil hot melt synthetic rubber adhesive	
Overall Thickness	1.9 mil (+/- 5%)	PSTC-33
Peel Adhesion	42.4 ounces per inch	PSTC-1
Tensile Strength	24.3 pounds per inch	PSTC-31
Elongation	120% at break	PSTC-31
Application Temperatures	32° F to 150° F	
Operating Temperatures	0° F to +200° F	
Recommended Storage	Temperature 72° F Humidity 50%	
Shelf Life	Over one year at recommended storage levels	
Government Spec	Complies with 40 CFR Part 82 and the Safe Drinking Water and Toxic Enforcement Act of 1986	

Ordering Information

Web Width	61.0"
Standard Length	5,000'
Custom Slitting	Available in 1/16" increments from 1/2" to 61.0" in lengths of 5,000'. Other lengths full web cut only. There is an up charge on widths less than 2".
Quick Response	Slit to order in NC, IL and CA. Orders generally ship in 24 hours. Orders placed before 12:00 PM eastern time may ship the same day.
Packaging	Packed in cartons. Larger quantity orders available in bulk pack on pallets.

IMPORTANT NOTICE TO BUYER: Replaces all prior spec sheets. All statements, information and recommendations herein are based on calculations and tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. Before using, user shall determine suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. Seller neither makes, nor shall be bound by, any warranty, expressed, implied, statutory or otherwise. The seller limits its obligation to replacement or, at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it. FilmLOC® is a registered trademark.

Sunbelt Sales and Marketing Associates, Inc.
Phone: 800-783-6258 or 404-892-8778
e-mail: info@sunbelt-sales.com

170 Ottley Drive Atlanta, GA 30324
Fax: 800-878-9886 or 404-874-1654
www.filmloc.com

