# #9615 SUPER BOND Woven PP Repair Tape for patching Super Sack® containers, bulk bags, FIBC's, bales, woven fabric and tarps; for strapping and banding

Effective 10.16.26

**Description**

High strength reinforced woven PP tape with an extremely aggressive adhesive. Repair tape for patching Super Sack containers, bulk bags, FIBC's, bales, woven fabric and tarps; for strapping and banding of various types of products that require extra strength; for seaming carpet backings for industrial and consumer use and for other industrial applications. Exceptional for use in applications that require extra strength and an aggressive adhesive. Easy to apply and approved for indirect food contact by FDA regulation title 21, subpart B, section 175.105. Can be sewn. Manufactured in the USA.

**Applications**

For patching bulk bags, FIBC's, bales, woven fabric and tarps; for strapping and banding; for seaming carpet backings; and for other industrial applications. Easy to apply. Can be sewn. Approved for indirect food contact by FDA regulation title 21, subpart B, section 175.105.

**Features**

- Has immediate high bonding strength
- Adheres well to rough or dirty surfaces
- Excellent long term adhesion strength
- Excellent puncture resistance

**Product Data**

| | |
|---|---|
| Film | 17 mil reinforced woven polypropylene fabric |
| Adhesive | 5 mil formulated rubber adhesive |
| Liner | 60# polysiiicone paper release liner |
| Overall Thickness | 22 mil (+/-5%) |
| Peel Adhesion (PSTC-101) | 155 ounces per inch width |
| Tack (ASTM D2979) | 34 ounces |
| Shear Strength (PSTC-107) | 300 minutes |
| Application Temperatures | $60^{O}$ F to $110^{O}$ F |
| Operating Temperatures | $-4^{O}$ F to $150^{O}$ F |
| Recommended Storage | Temperature $72^{O}$ F 50% humidity |
| Shelf Life | One year at recommended storage levels |

FILMLOC

www.filmloc.com • p. 404.892.8778

FilmLOC Inc. 5470 Oakbrook Pkwy Suite A Norcross, GA 30093